

14 October 2019 r.

*Object:* **Test report PU FEST 2K**

Below are the tests carried out on our two-component water-based finish.

Determination of the anti-slip properties – Workrooms and fields of activities with raised slip danger, walking method – ramp test

Surface characteristics: Rough

**OPERATIVE CONDITIONS:**

Temperature:  $(23 \pm 5)^{\circ}\text{C}$

Fixing scheme: see attachment

**RESULTS**

Average total acceptance angle:  $11,8^{\circ}$

Movement area ( $\text{cm}^3/\text{dm}^2$ ): not determined

**CLASSIFICATION (BGR 181 – 10/2003)**

Group of anti – slip properties: R10

Movement area evaluation group: not determined





walking  
direction

